

N700A

Non-Silicone Thermal Conductive Pad

Non-Silicone Thermal Compound N700A is made of non-silicon resin material. No low-molecular-weight siloxane volatilization, no electrical contact & pollution problems. N700A is flexible and has great thermal conduction, making the thermal resistance as low as possible. The thermal conductivity is 1.5W/m*K. It's suitable for optical and sensitive electric components.

■ FEATURES

- / Thermal conductivity:1.5 W/m*K
- / It's made by non-silicone resin materials
- / Low contact thermal resistance
- / With electrical insulation
- / Outstanding thermal conductivity
- / Applicable to optical and sensitive electric components

■ TYPICAL APPLICATION


/ HDDS

/ Optical appliance

■ SPECIFICATIONS

/ Sheet form

/ Die-cut parts




■ TYPICAL PROPERTIES

			I
PROPERTY	N700A	TEST METHOD	UNIT
Color	Gray	Visual	-
Surface tack 2-side/1-side	2	-	-
Thickness	Customized	ASTM D374	mm
Density	2.2	ASTM D792	g/cm³
Hardness	60	ASTM D2240	Shore OO
Application temperature	-60~125	-	°C
ROHS & REACH	Compliant	-	-
COMPRESSION@1.0mm			
Deflection @10 psi	10	ASTM D5470 modify	%
Deflection @20 psi	26	ASTM D5470 modify	%
Deflection @30 psi	43	ASTM D5470 modify	%
ELECTRICAL			
Dielectric breakdown	10	ASTM D149	KV/mm
Surface resistivity	>1011	ASTM D257	Ohm
Volume resistivity	>1010	ASTM D257	Ohm-m
THERMAL			
Thermal conductivity	1.5	ASTM D5470	W/m*K
Thermal impedance@10 psi	0.708	ASTM D5470	°C-in²/ W
Thermal impedance@20 psi	0.445	ASTM D5470	°C-in²/ W
Thermal impedance@30 psi	0.293	ASTM D5470	°C-in²/ W
memai impedance@30 psi	0.293	A3 10 D3470	C-111 / VV

The chemical formula indicates that if Cyclic polydimethylsilox-ane $(HO-[Si(CH_3)_2O]_n-H)$ is non-reaction, it's volatile anytime and everywhere. For example, when the electric products which has been put in a confined space, the volatile of low-molecular-weight silox-anes will makes the elecetic products uncontacted.

Thermal Resistance vs. Pressure vs. Deflection



Note: All specifications provided by LiPOLY are subject to change without notice. The test methods used by LiPOLY are based on the TIM Tester method and ASTM D5470 test method. These test methods are used as the definition standards for LiPOLY. Property values provided in this document are not for product specifications or guaranteed. This document does not guarantee the performance and quality required for the purchaser's specific purpose. The purchaser needs to evaluate and verify the safety before using the material. We strongly recommend the purchaser pre-test the product and verify the performance of the product under the purchaser's specific conditions. Liability and use of the product are the responsibility of the end user. LiPOLY makes no warranty as to the suitability, merchantability, or one-infringement of any LiPOLY material or product for any specific or general uses. LiPOLY shall not be liable for incidental orconsequential damages of any kind. All LiPOLY products are sold in accordance with the LiPOLY Terms and Conditions in effect at the time of purchase and a copy of which will be furnished upon request. All rights reserved, including LiPOLY trademarks or registered trademarks of LiPOLY or its affiliates. Statements concerning possible or suggested uses made herein shall not be relied upon or be constructed as a guaranty of patent infringement. Copyright 2022 LiPOLY.