

T-top98-s

High Thermal Conductive Gap Filler

LiPOLY T-top98-s offers outstanding thermal conductivity at 18.0 W/m*K and extremely low thermal resistance under minimal force. T-top98-s offers excellent compression, filling small air gaps on uneven surfaces, ensuring an efficient and consistent transfer of heat.

■ FEATURES

- / Thermal conductivity: 18.0 W/m*K
- / High compression rate
- / Extremely low thermal impedance

■ TYPICAL APPLICATION

- / Between CPU and heat sink
- / Between a component and heat sink
- / Flat-panel displays
- / Power supplies
- / High speed mass storage drives
- / Telecommunication hardware
- / 5G base station & infrastructure
- / EV electric vehicle



■ CONSTRUCTION

Series	Characteristics	Configurations
T-top98-s	Silicone compound with weak sticky surfaces.	Sheets form, Die-cuts parts

■ TYPICAL PROPERTIES

PROPERTY	T-top98-s	TEST METHOD	UNIT
Color	Purple	Visual	-
Surface tack 2-side/1-side	2	-	-
Thickness	Customized	ASTM D374	mm
Density	3.3	ASTM D792	g/cm ³
Hardness	65	ASTM D2240	Shore 000
TML	<0.1	By LiPOLY	%
Application temperature	-60~150	-	°C
ROHS & REACH	Compliant	-	-

COMPRESSION

Deflection @10 psi	11	ASTM D5470 modify	%
Deflection @20 psi	38	ASTM D5470 modify	%
Deflection @30 psi	62	ASTM D5470 modify	%
Deflection @40 psi	71	ASTM D5470 modify	%
Deflection @50 psi	77	ASTM D5470 modify	%

ELECTRICAL

Dielectric breakdown	8	ASTM D149	KV/mm
Surface resistivity	>10 ¹¹	ASTM D257	Ohm
Volume resistivity	>10 ¹⁰	ASTM D257	Ohm-m
Dielectric constant@10MHz D _k	10.0	ASTM D150	-
Dielectric constant@1GHz D _k	9.9	ASTM D150	-
Dielectric constant@1.8GHz D _k	10.3	ASTM D150	-
Dielectric factor@10MHz D _f	0.003	ASTM D150	-
Dielectric factor@1GHz D _f	0.007	ASTM D150	-
Dielectric factor@1.8GHz D _f	0.025	ASTM D150	-

THERMAL

Thermal conductivity	18.0	ASTM D5470	W/m*K
Thermal conductivity	10.5	ISO 22007-2	W/m*K
Thermal impedance@10psi	0.149	ASTM D5470	°C-in ² / W
Thermal impedance@20psi	0.104	ASTM D5470	°C-in ² / W
Thermal impedance@30psi	0.061	ASTM D5470	°C-in ² / W
Thermal impedance@40psi	0.046	ASTM D5470	°C-in ² / W
Thermal impedance@50psi	0.039	ASTM D5470	°C-in ² / W
Coefficient of thermal expansion	-312.13x10 ⁻⁶	ASTM E228	1/K

■ THERMAL IMPEDANCE & COMPRESSION

Compression Force (psi)	Thermal Impedance (°C-in²/W)			Compression (%)		
	1.0 mm	2.0 mm	3.0 mm	1.0 mm	2.0 mm	3.0 mm
10	0.149	0.247	0.304	11	20	39
20	0.104	0.138	0.156	38	58	71
30	0.061	0.085	0.080	62	75	82
40	0.046	0.064	0.065	71	83	87
50	0.039	0.046	0.054	77	86	90

Test method: ASTM D5470

■ RELIABILITY

Test Property	Compression Force (psi)	70°C				
		Initial	100 hrs	250 hrs	500 hrs	1000 hrs
Thermal Resistance	10	0.149	0.148	0.149	0.148	0.149
	30	0.061	0.061	0.061	0.062	0.062
	50	0.039	0.039	0.038	0.038	0.039

Test Property	Compression Force (psi)	150°C				
		Initial	100 hrs	250 hrs	500 hrs	1000 hrs
Thermal Resistance	10	0.149	0.148	0.149	0.149	0.150
	30	0.061	0.061	0.061	0.062	0.062
	50	0.039	0.039	0.039	0.040	0.040

Test Property	Compression Force (psi)	60°C / 90%RH				
		Initial	100 hrs	250 hrs	500 hrs	1000 hrs
Thermal Resistance	10	0.149	0.148	0.149	0.148	0.149
	30	0.061	0.061	0.060	0.061	0.061
	50	0.039	0.039	0.038	0.040	0.040

Test Property	Compression Force (psi)	-40°C (30min) ↔ +125°C (30min)					
		0 Cycles	100 Cycles	200 Cycles	300 Cycles	400 Cycles	500 Cycles
Thermal Resistance	10	0.149	0.148	0.149	0.148	0.149	0.148
	30	0.061	0.060	0.061	0.060	0.061	0.061
	50	0.039	0.038	0.039	0.038	0.038	0.039

Test Property	Compression Force (psi)	Ultra Low Temperature -60°C					
		Initial	100 hrs	200 hrs	300 hrs	400 hrs	500 hrs
Thermal Resistance	10	0.149	0.148	0.148	0.148	0.149	0.149
	30	0.061	0.060	0.061	0.060	0.061	0.061
	50	0.039	0.039	0.038	0.039	0.040	0.040

Test method: ASTM D5470 , Specimen thickness = 1.0mm , Unit: °C-in²/W

Note: All specifications provided by LiPOLY are subject to change without notice. The test methods used by LiPOLY are based on the TIM Tester method and ASTM D5470 test method. These test methods are used as the definition standards for LiPOLY. Property values provided in this document are not for product specifications or guaranteed. This document does not guarantee the performance and quality required for the purchaser's specific purpose. The purchaser needs to evaluate and verify the safety before using the material. We strongly recommend the purchaser pre-test the product and verify the performance of the product under the purchaser's specific conditions. Liability and use of the product are the responsibility of the end user. LiPOLY makes no warranty as to the suitability, merchantability, or non-infringement of any LiPOLY material or product for any specific or general uses. LiPOLY shall not be liable for incidental or consequential damages of any kind. All LiPOLY products are sold in accordance with the LiPOLY Terms and Conditions in effect at the time of purchase and a copy of which will be furnished upon request. All rights reserved, including LiPOLY trademarks or registered trademarks of LiPOLY or its affiliates. Statements concerning possible or suggested uses made herein shall not be relied upon or be constructed as a guaranty of patent infringement. Copyright 2023 LiPOLY.