

NL-putty06-s

Non-Silicone Lightweight Thermal Conductive Putty

LiPOLY's NL-putty06-s is a non-silicone, low-density gap filling material without volatile low-molecular-weight siloxane volatile, low total volatile gas. It is suitable for electronic products and automotive electronic devices. Its low density and lightweight characteristics improve product performance, reduce production costs, and minimize material usage and energy consumption. With a thermal conductivity of 6.0 W/m*K and high deformability, it can flexibly adapt to gap and has tolerance compensation properties. It can overcome overflow and drying problems, improve heat conduction, and is suitable for automated dispensing production.

■ FEATURES

- / Lightweight, Low Density,
Thermal Conductivity: 6.0 W/m*K
- / High flow rate, extrusion rate under
90psi&60s conditions: 28 g/min
- / Bond line thickness:100-1500μm
- / Non-silicone resin materials
- / Designed to remove manufacturing
tolerances
- / Does not produce stress on delicate
components
- / No vertical flow
- / Dispensable for serial manufacture
- / For any high compression and low
stress application

■ TYPICAL APPLICATION

- / lightweight applications, such as
Automotive electronic devices, Mobile
communication device, Drone &
aircraft,Sports and leisure electronic
products, Portable computers and
tablets,wearable devices, Portable
game consoles, VR devices and etc.

■ CONFIGURATIONS

- / Cartridges: 30ml, 150ml
- / Bucket: 1kg, 25kg

■ PRESERVATION


It can be preserved for 60 months
under the condition of unopened
and under room temperature 25°C.

■ TYPICAL PROPERTIES

PROPERTY	NL-putty06-s	TEST METHOD	UNIT
Color	Purple	Visual	-
Resin base	Non-Silicone	-	-
Viscosity	6000	DIN 53018	Pa.s
Flow Rate (30cc EFD tube, 2.35mm Orifice diameter, 90psi&60s)	28	By LiPOLY	g/min
Density	2.6	ASTM D792	g/cm ³
Application temperature	-60~125	-	°C
Bond line thickness	100~1500	-	μm
Shelf life	60 months	-	-
ROHS & REACH	Compliant	-	-
ELECTRICAL			
Dielectric breakdown	13	ASTM D149	KV/mm
Volume resistivity	>10 ¹¹	ASTM D257	Ohm-m
THERMAL			
Thermal conductivity	6.0	ASTM D5470	W/m*K
Thermal impedance@10psi / 80°C	0.059	ASTM D5470	°C-in ² / W
Thermal impedance@30psi / 80°C	0.054	ASTM D5470	°C-in ² / W
Thermal impedance@50psi / 80°C	0.049	ASTM D5470	°C-in ² / W

■ VERTICAL RELIABILITY

sing 1.5mm pad as a gap control, put the putty between the
aluminum and the glass panel mark the initial position. Then,
place it in the oven with 125°C for 1,000 hours and observe its
displacement after reliability test



Material no dropped or changed after
high temperature aging testing